

Eppendorf Certificate

Certificate of Quality

Eppendorf Plates® – Typical values for trace metals

The values in the table indicate typical values of trace metal concentrations obtained by incubating Eppendorf Plates with concentrated nitric acid for 1 hour (see Materials and Methods).

As the indicated values were determined in a one-time measurement they cannot be guaranteed for every lot of Eppendorf Plates. Rather they give an idea to what extent trace elements can be eluted from Eppendorf Plates.

	Trace metal release [ng/μl]								
	Al	Cd	Cr	Cu	Hg	Mn	Ni	Pb	Zn
Eppendorf Microplates									
96/F	0.029	<0.00002	0.00064	0.0022	<0.001	0.00054	0.00036	0.00059	0.008
96/U	0.028	<0.00002	0.00062	0.0021	<0.001	0.00052	0.00035	0.00058	0.008
96/V*	0.028	<0.00002	0.00063	0.0022	<0.001	0.00053	0.00036	0.00059	0.008
384/F	0.048	0.00003	0.00108	0.0037	<0.001	0.00090	0.00061	0.00100	0.014
384/V*	0.047	0.00003	0.00105	0.0036	<0.001	0.00088	0.00059	0.00098	0.013
Eppendorf Deepwell Plates									
384/200 μl*	0.049000	0.000030	0.001100	0.003800	<0.001	0.000920	0.000620	0.001020	0.014000
96/500 μl*	0.027591	0.000017	0.000619	0.002140	<0.001	0.000518	0.000349	0.000574	0.007883
96/1000 μl*	0.027297	0.000017	0.000613	0.002117	<0.001	0.000513	0.000345	0.000568	0.007799
96/2000 μl*	0.021787	0.000013	0.000489	0.001690	<0.001	0.000409	0.000276	0.000454	0.006225
Protein LoBind® Plates									
384/200 μl	0.008000	<0.00002	0.000110	0.000400	<0.001	0.000140	0.000070	0.000160	0.013000
384/V-PP	0.007668	<0.00002	0.000105	0.000383	<0.001	0.000134	0.000067	0.000153	0.012461
96/500 μl	0.004505	<0.00002	0.000062	0.000225	<0.001	0.000079	0.000039	0.000090	0.007320
96/1000 μl	0.004457	<0.00002	0.000061	0.000223	<0.001	0.000078	0.000039	0.000089	0.007242
DNA LoBind® Plates									
384/200 μl	0.015000	0.000030	0.000130	0.000700	<0.001	0.000042	0.000070	0.000100	0.007000
384/V-PP	0.014378	0.000029	0.000125	0.000671	<0.001	0.000403	0.000067	0.000096	0.006710
96/500 μl	0.008446	0.000017	0.000073	0.000394	<0.001	0.000236	0.000039	0.000056	0.003942
96/1000 μl	0.008356	0.000017	0.000720	0.000390	<0.001	0.000234	0.000039	0.000056	0.003900
96/V-PP	0.008648	<0.00002	0.000075	0.000404	<0.001	0.000242	<0.00005	0.000058	0.004036

* applies also to the SafeCode variants

Page 1 of 2

Eppendorf Certificate

	Trace metal release [ng/μl]								
	Al	Cd	Cr	Cu	Hg	Mn	Ni	Pb	Zn
Eppendorf twin.tec® PCR Plates									
384 skirted*	0.000379	<0.00002	<0.00005	<0.00010	<0.001	0.000123	<0.00005	<0.00005	<0.0010
384 microbiology	0.002000	<0.00002	<0.00005	<0.00010	<0.001	0.000123	<0.00005	<0.00005	<0.0010
96 semi-skirted	0.001300	<0.00002	<0.00005	<0.00010	<0.001	0.000070	<0.00005	<0.00005	<0.0010
96 skirted*,*1	0.001420	<0.00002	<0.00005	<0.00010	<0.001	0.000076	<0.00005	<0.00005	<0.0010
96 unskirted 150 μl	0.001420	<0.00002	<0.00005	<0.00010	<0.001	0.000076	<0.00005	<0.00005	<0.0010
96 unskirted 250 μl	0.001300	<0.00002	<0.00005	<0.00010	<0.001	0.000070	<0.00005	<0.00005	<0.0010
Eppendorf twin.tec® PCR Plates LoBind®									
96 semi-skirted	0.003300	<0.00002	<0.00005	<0.00002	<0.00005	<0.00010	<0.001	<0.00005	<0.00005
96 skirted	0.003605	<0.00002	<0.00005	<0.00002	<0.00005	<0.00010	<0.001	<0.00005	<0.00005

Materials and Methods

Eppendorf Plates were filled with their nominal volume using concentrated nitric acid (65 %) and incubated for 1 hour at room temperature (20 °C). The eluate was then analyzed by inductively coupled plasma mass spectrometry (ICP-MS). The trace metal concentrations are expressed in ng/μL. The values represent an average of three individually analyzed samples. All values labeled with "<" indicate concentrations below the detection limit of the ICP-MS method. The trace metal release of the remaining Eppendorf Plates were calculated from their surface/volume ratio.

No metal release was observed after 5-10 times rinsing with concentrated nitric acid or after rinsing with 10 % acetic acid or water. All analyses were performed by an independent laboratory accredited according to ISO/IEC 17025.

Hamburg, September 2023

* applies also to the SafeCode variants
*1 applies also to the BioBased variants

Page 2 of 2

Joana Tziolis
Product Life Cycle Manager
Division Consumables

Monika Schneider
Vice President Global Quality Management &
Regulatory Affairs

Your local distributor: www.eppendorf.com/contact
Eppendorf SE · Barkhausenweg 1 · 22339 Hamburg · Germany
E-mail: eppendorf@eppendorf.com

ISO 9001
Certified

ISO 13485
Certified

ISO 14001
Certified

Eppendorf® and the Eppendorf Brand Design, Eppendorf Plates®, Eppendorf twin.tec® and LoBind® are registered trademarks of Eppendorf SE, Germany. All rights reserved. incl. graphics and images. Copyright ©2023 by Eppendorf SE.